

Baumit SEP 01-04

Topcoat render

Product Factory prepared dry powder mortar in accordance with EN 998-1. Mineral based decorative topcoat render for thin coat application for internal and external areas. Suitable for hand or machine application.

Composition White lime, white cement, sand and additives to improve workability and adhesion. Coloured Baumit SEP contains additional lime, cement and light fast pigments.

Properties Mineral based, weather resistant, water vapour and CO₂ permeable, stain resistant, and easy to use. Different grain sizes, 1mm, 2mm, 3mm and 4mm, gives a choice of wet dash or dragged grain textures.

Intended use A topcoat render providing decoration and protection to facades and internal areas. For application over lime and cement render basecoats, contact mortars, EWI basecoats, concrete surfaces and gypsum plaster and gypsum plasterboard.

Technical data

Designation:	CS II acc. to EN 998-1
Aggregate size:	1.0/2.0/3.0/4.0 mm
Compression strength:	> 1.5 - 5.0 N/mm ²
Thermal conductivity λ _{10, dry} :	≤ 0.89 W/mK (P = 90%, tabulated) ≤ 0.82 W/mK (P = 50%, tabulated)
Bond strength:	≥ 0.08 N/mm ²
Water vapour diffusion resistance μ:	≤ 20
Capillary water absorption :	W 2 (EN 998-1)
Minimum layer thickness:	applied to grain size (min. 2 mm)

ScheibenPutz SEP	SEP 01	SEP 02	SEP 03	SEP 04
Grain size [mm]:	0 - 1	0 - 2	0 - 3	0 - 4
Water requirement [l/sack]:	6.5 - 7.5	6.0 - 7.0	6.0 - 7.0	5.5 - 6.5
Consumption ca. [kg/m ²]:	2.2/2 mm	3.3/2 mm	4.0/3 mm	5.5/4 mm
Yield ca. [m ² / sack]:	11.4	7.6	6.3	4.5

The consumption rates serve for guidance only. An allowance of 10% more consumption should be calculated in practice.

Health and safety Please refer to the Material Safety Data Sheet, produced in accordance with Article 31 and Annex II of Regulation No 1907/2006 of the European Parliament and Council from 18.12.2006, available at www.baumit.com or alternatively request the MSDS from the manufacturer.

Storage Store in dry, cool conditions, free from frost in sealed tubs. Shelf life 12 months.

Quality assurance In house monitoring through our own laboratories. Third party inspection is carried out through a certified body.

Packaging Sacks 25 kg. 1 pallet = 42 sacks = 1050 kg.

Substrate Substrates must be sound, clean, dry, free from frost, dust efflorescence and not hydrophobic. Render basecoats must be flat, well keyed, dry and fully cured. Allow for drying times of 1 day per mm thickness for render base coats. Smooth concrete surfaces should receive a keyed bonding coat using a suitable contact mortar (for example Baumit MC 55 W or StarContact). Backgrounds at risk of leaching and staining (plasterboard, nicotine stains etc) must be sealed with Baumit SperrGrund (2 coats). Friable basecoats must be treated with Baumit PutzFestiger stabiliser. Allow to dry for 24 hours. Refer to Baumit for advice regarding other substrates and substrate preparation.

Application

High suction substrates, gypsum plasters and plasterboards should be primed with a full and even coat of Baunit PremiumPrimer DG 27 (undiluted) before applying Baunit SEP. Allow to dry for 24 hours. Refer to Product Data Sheet.

Mixing:

Baunit SEP powder must be well and slowly mixed in a tub of clean water with an electric hand mixer to a creamy workable consistency. Automated continuous horizontal mixers may also be used. For small areas the mixed render can be manually applied. For larger areas the fresh render can be fed into a mortar pump for spray application. Alternatively, mortar mixing pumps provide an all-in-one mixing and spraying solution.

Application:

Baunit SEP topcoat render is applied onto the substrate to the required thickness and trowelled through to the grain thickness to produce a full and even coat. The surface is then textured using a coarse sponge float or plastic float according to desired finish, moving in tight circular motions. Baunit SEP is suitable for freestyle texturing and soft brushing with a little water.

Baunit SEP should be applied systematically and continuously in complete sections.

It is recommended that all Baunit mineral renders are treated with two coats of a suitable paint (for example Baunit ArtLine Silicon) to protect against variations in appearance due to differential drying out and weathering of the facade.

Further information

The air, material and background temperature must be above +5° C during application and curing. Protect the facade from direct sunlight, rain and strong winds (i.e. with scaffold nets). High air humidity and low temperatures can prolong drying times considerably.

Coloured products from different batches must be mixed together prior to application.

Colour tone development can be affected by the background conditions, temperature and air humidity level

The sands used in the Baunit facade renders are natural products. On occasion some of the sand grains may appear slightly darker. This does not in any way constitute a problem with quality of the product, but may represent a faint optical detractor, due to the natural properties of the raw materials.

A Light Reflectance Value lower than 25 must not be used for application on to External Wall Insulation systems.

Baunit SEP should be left to dry for at least 5 days (at +20 C° and 60 % rel. humidity) before receiving any further coatings.

Protective measures: Protect eyes and skin, and surrounding areas, especially glass, ceramic, brick, natural stone, varnishes and metals. Wash away any splashes with plenty of water. Do not allow to dry and harden.

Clean tools and equipment thoroughly with water immediately after use.

The information contained in this product data sheet together with any additional written or verbal information provided by Baunit is based on Baunit's previous experience of this product and reflects Baunit's current understanding of the properties of the product. However, the Customer acknowledges that the advice given in this product data sheet is not intended to be legally binding nor to create any obligation which is legally enforceable against Baunit. It is the customer's responsibility to make its own enquires and investigations into the properties and use of this product and to verify that the product is fit for the customer's intended use. Baunit reserves the right to make changes to the product without prior notice.

Baunit UK Ltd 4200 Waterside Centre, Solihull Parkway Birmingham Business Park, Birmingham. B37 7YN
tel.: +44 (0) 333 358 3434, email: info@baunit.co.uk, web.: www.baunit.co.uk